



Technical datas Film Faced PLYWOOD 15mm					
NO	Property		Unit	Test Method	Value of Test
1	Moisture Content		%	EN322	8-12
2	Density		kg/m ³	EN322	530
3	Bonding Quality	Bonding Quality	Mpa	EN314	Max: 1.29 Min: 0.82
		Damage Rate	%	GB/T17656-2015	60%
4	Bending Modules of Elasticity	Longitudinal	Mpa	EN310	8560
		Lateral			6850
5	Bending Strength	Longitudinal	Mpa	EN310	72
		Lateral			51

Со почит,

