



Technical datas FilmFaced PLYWOOD 21mm					
NO	Property		Unit	Test Method	Value of Test
1	Moisture Content		%	EN322	8-12
2	Density		kg/m ³	EN322	530
3	Bonding Quality	Bonding Quality	Mpa	EN314	Max: 1.72 Min: 0.85
		Damage Rate	%	GB/T17656-2015	60%
4	Bending Modules of Elasticity	Longitudinal	Mpa	EN310	6800
		Lateral			5920
5	Bending Strength	Longitudinal	Mpa	EN310	63
		Lateral			48

Со почит,

